THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM

EA 9394 AERO — structural paste adhesive

A structural adhesive is stiff, carries load and cures hard.

Designation

Item	Value
Designation	EA 9394 AERO
Class	Chemicals
Type	structural paste adhesive

EA 9394 AERO properties (Henkel bulletin)

Property	Value
Cure at 77 F	3 to 5 days for normal performance
Accelerated cure	Up to 200 F (93 C), small masses only
Glass transition, dry	78 C (172 F)
Glass transition, wet	68 C (154 F)
Hardness at room temperature	Shore D 88

Henkel LOCTITE EA 9394 AERO technical process bulletin. Check the revision in use.

Notes

- **One adhesive.** Only EA 9394 AERO is given, and only the figures we read.
- **No mix ratio or pot life** for it; read the TDS.
- **No film adhesives.** We did not find a public sheet to cite.

SOURCES · Henkel, LOCTITE EA 9394 AERO technical process bulletin · FAA AC 43.13-1B CHG 1, Chapter 6

SCAN · OPEN THIS DATA SHEET
theaviationpoint.com/parts/materials/ea-9394/

Reference data. The aircraft manufacturer's documentation (SRM / IPC) takes precedence.