THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM


3003 Aluminum

Soft and easy to work, and used like 1100 where strength is not the point: tanks, cowlings, tubing.

REFERENCE DRAWING — NOT APPROVED DATA · THE SRM ALWAYS GOVERNS

THE MARKING

ALLOY NUMBER, THEN TEMPER



SERIES

FIRST DIGIT: MAIN ALLOYING ELEMENT

SERIES	ELEMENT	EXAMPLES
1xxx	Aluminum, 99 % or more	1100
2xxx	Copper	2024, 2219
3xxx	Manganese	3003
5xxx	Magnesium	5052, 5086
6xxx	Magnesium and silicon	6061, 6063
7xxx	Zinc	7075, 7050

BASIC TEMPER LETTERS

AC 43.13-1B TABLE 4-4

LETTER	MEANING
F	As fabricated. No property limits
O	Annealed: the softest temper
H	Strain-hardened (non heat-treatable)
T	Heat-treated to a stable temper

PARTS LIST

#	WHAT IT SAYS
1	Alloy number: the composition
2	T: heat-treated
3	3: solution treated, cold-worked
4	51: stretched 1 to 3 % set

NOTES

1. Dimensions in inches. Do not scale: the SRM sets the values.
2. For reference. The applicable manual always governs.
3. Based on AC 43.13-1B Table 4-4, AA Teal Sheets.

REVISIONS

REV	DESCRIPTION	DATE
A	First issue	2026-10-30

The Aviation Point. Structural repair reference

TITLE: Aluminum alloy and temper code

DRAWING NO.	REV	SCALE	SHEET
TAP-DWG-047	A	NTS	1 OF 1

APPLIES TO: Wrought aluminum alloys

DO NOT SCALE DRAWING

Temper meanings from AC 43.13-1B Table 4-4. Full list: aluminum temper chart.

Key facts

Property	Value	Source
Density	0.099 lb/in³ (2.73 g/cm³)	Teal Sheets
Brinell hardness, O / H16	28 / 47	AC 43.13-1B Table 4-5
Tempers	H, strain-hardened	AC 43.13-1B Table 4-4
Fuel tank repair	May be repaired by welding	AC 43.13-1B par. 8-32
Rivets for it	1100	AC 43.13-1B par. 7-2c

Composition limits, weight percent

Element	Limit
Si	0.6
Fe	0.7
Cu	0.05–0.20
Mn	1.0–1.5
Zn	0.10
Al	Remainder

Key points

- **Not a source of design allowables.** Values are for reference. MMPDS and the SRM govern a repair.
- **Not a substitution approval.** A different alloy or temper needs approved data.
- **No strength values here.** The public sources used for this site do not print them.

SOURCES · FAA AC 43.13-1B CHG 1, Chapters 4 and 7 · FAA-H-8083-31B, AMT Handbook — Airframe, Volume 1, Chapter 4 · Aluminum Association, International Alloy Designations, rev. Aug 2018

SCAN · OPEN THIS GUIDE
theaviationpoint.com/materials/aluminum/3003/

Educational reference only, not approved data. Always consult the applicable SRM, AMM, or AC 43.13-1B and your certifying authority.

THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM · THE AVIATION POINT · THEAVIATIONPOINT.COM